

# QUALITY CERTIFICATE-TDS



# N375



QUALITY SPECIFICATION	ASTM TEST METHOD	RESULT
IODINE ADSORPTION NUMBER (g/kg)	D 1510	90±5
OIL ADSORPTION NUMBER (OAN) , (ml/100g)	D 2414	114±5
POUR DENSITY , ( Kg/m³)	D 1513	345±20
HEATING LOSS (max %)	D 1509	1
TOLUENE SOLVENT DISCOLORATION , (MIN%)	D 1618	85
PH	D 1512	7.5 - 9
FINES CONTENT - QBAG.(MAX%)	D 1508	7
FINES CONTENT - BAG.(MAX%)	D 1508	10
INDIVIDUAL PELLET HARDNESS-Max 20, (CN)	D 3313	50
INDIVIDUAL PELLET HARDNESS-Ave 20, (CN)	D 3313	10 - 40
SIEVE RESIDUE -NO 35 US Std max , (ppm)	D 1514	10
SIEVE RESIDUE -NO 35 US std , (ppm)	D 1514	1000
ASH CONTENT (MAX %)	D 1506	0.75

## Soft Grades

N-550 SHP-50

N-660 SHP-60

N-772



## Hard Grades

N-220 N-234

N-330 N-375

N-339 N-326

SHP-100

DIBA TICARET İTHALAT İHRACAT LTD. ŞTİ

Cumhuriyat Mah . Gürpınar Yolu Cad, Eresin Merkezi , A Blok , Kat 8 .Ofis No 144 / Büyükçekmece/ İSTANBUL

sales@dibaticaret.com

www.dibaticaret.com

T: +90 552 554 38 34

W: +905315678909