

QUALITY CERTIFICATE-TDS



N550




| QUALITY SPECIFICATION | ASTM TEST METHOD | RESULT |
|---|------------------|---------|
| IODINE ADSORPTION NUMBER (g/kg) | D 1510 | 43±5 |
| OIL ADSORPTION NUMBER (OAN) , (ml/100g) | D 2414 | 121±5 |
| POUR DENSITY , (Kg/m³) | D 1513 | 360±20 |
| HEATING LOSS (max %) | D 1509 | 1 |
| TOLUENE SOLVENT DISCOLORATION , (MIN%) | D 1618 | 75 |
| PH | D 1512 | 7.5 - 9 |
| FINES CONTENT - QBAG.(MAX%) | D 1508 | 7 |
| FINES CONTENT - BAG.(MAX%) | D 1508 | 10 |
| INDIVIDUAL PELLET HARDNESS-Max 20, (CN) | D 3313 | 50 |
| INDIVIDUAL PELLET HARDNESS-Ave 20, (CN) | D 3313 | 10 - 40 |
| SIEVE RESIDUE -NO 35 US Std max , (ppm) | D 1514 | 10 |
| SIEVE RESIDUE -NO 35 US std , (ppm) | D 1514 | 1000 |
| ASH CONTENT (MAX %) | D 1506 | 0.75 |

Soft Grades

N-550 SHP-50

N-660 SHP-60

N-772



Hard Grades

N-220 N-234

N-330 N-375

N-339 N-326

SHP-100

DIBA TICARET İTHALAT İHRACAT LTD. ŞTİ

Cumhuriyat Mah . Gürpınar Yolu Cad, Eresin Merkezi , A Blok , Kat 8 .Ofis No 144 / Büyükçekmece/ İSTANBUL

sales@dibaticaret.com

www.dibaticaret.com

T: +90 552 554 38 34

W: +905315678909